

CONNECTICUT

GRADATION OF AGGREGATE

MAIN: (973) 595-6250
CENTRAL DISPATCH: (973) 595-6130
FAX: (973) 595-7087
SERVICE@BRAENSTONE.COM
BRAENSTONE.COM

PERCENTAGE PASSING BY WEIGHT (MASS)

Square Mesh Sieves	No. 3	No. 4	No. 6	No. 67	No. 8	Screenings	Dust
2 ½" (63 mm)	100						
2" (50 mm)	90-100	100					
1 ½" (37.5 mm)	35-70	90-100					
1" (25 mm)	0-15	20-55	100	100			
¾" (19 mm)		0-15	90-100	90-100			
½" (12.5 mm)	0-5		20-55		100		
⅜" (9.5 mm)		0-5	0-15	20-55	85-100	100	
No. 4 (4.75 mm)			0-5	0-10	10-30		100
No. 8 (2.36 mm)				0-5	0-10	60-100	40-100
No. 16 (1.18 mm)					0-5		

Reclaimed miscellaneous aggregate shall only be used where authorized in the specifications.